


Nature of the investigation:


Laboratory Sound Absorption Test

The examined structure:
2mm Zorin material, 100mm air gap behind it,
edge damping on the side



Date of examination:
31/01/2020
Principal:
Multifelt Factory Kft.
Headquarters: 9730 Kőszeg, Róti
Völgy u. 3.

2mm Zarin, side edge damping,
100mm minimum sound absorption factor



Weighted sound absorption factor:
 $\alpha_w = 0,80$ (H)

f[Hz]	250	500	1000	2000	4000
α (converted soundstage)	0.51	0.99	0.98	1	0.99